




Chemlease® PMR LS EU

Solvent-Based Semi-Permanent Release Agent



©2016 Chem-Trend L.P.

Description

Chemlease® PMR LS EU is the latest evolution of the trusted PMR family of semi-permanent release agents for composites molding applications. Chemlease® PMR LS EU is a low slip semi-permanent release agent specifically formulated for molding applications where pre-release of gel-coat is a concern. Chemlease® PMR LS EU also promotes the adhesion of most standard fine line masking, bag sealant and double-sided tapes. Chemlease® PMR LS EU is an ideal choice for releasing flat and concave shaped parts, while maintaining a Class A, high gloss mold finish.

Benefits

- Multiple releases between applications
- Minimizes pre-release potential
- Excellent tape adhesion
- Provides superior gloss
- Minimal transfer to the molded part

Mold Preparation

1. Mold surfaces should be thoroughly cleaned to remove all traces of wax, release agents, sealers and buffing compounds. Do a final cleaning of mold surface with the appropriate Chemlease® Mold Cleaner.
2. It is not necessary to seal the mold with a traditional mold sealer. If, however the mold is very porous, such as with tooling boards or 3D printed substrates, treatment with the appropriate Chemlease® mold primer is recommended, prior to application of release agent.

Application

1. Saturate clean cotton cloth (not dripping) and wipe on a smooth continuous film. Apply no more than a few square feet at a time.
2. When the film begins to evaporate at the edge, wipe the surface with a second clean dry cotton cloth. Use a circular motion from the outside, working inwards until film is left dry and clear. See **Note**.
3. Continue in this manner until entire mold surface has been covered.
4. Apply 5 - 7 total coats, allowing a minimum of 15 minutes to cure between each complete coat.
5. Allow 30 minutes for full cure, prior to gel coat application, layup, or molding.
6. When release becomes difficult, reapply 1 or more coats of Chemlease® PMR LS EU in the same manner, allowing 15 minutes between and 30 minutes after the final coat.

Note

Time will vary with room and mold temperature. Wipe off as the solvent begins to evaporate. If the release agent is left on too long, you may notice some smearing or streaking. To remove the smear or streak, wipe the affected area with the same Chemlease® release agent, then wipe off the area immediately following.

Important

The recommended number of coats and cure times are a general guideline found to be more than sufficient in a broad spectrum of molding conditions. When molding products with extreme geometries or experiencing low-humidity conditions in the shop, the customer may find the need to extend the cure time between coats and increase the number of coats applied to the mold. The efficiency of a release film is best determined through a combination of tape tests and experimentation.

Storage

Do not store at temperatures above 49°C/120°F. Keep container tightly sealed to prevent evaporation and/or contamination. If stored in cold temperatures allow warming to room temperature before using.

Packaging

Chemlease® PMR LS EU is available in a variety of package sizes. Please contact Chem-Trend customer service for details.

Safety Data

Safety Data Sheets are available for all Chemlease® products and should be consulted prior to use of the product.

Further Information

Request information on our complete range of materials for this industry.

Legal Notice

The technical information and suggestions for use contained herein is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a professional with technical experience. It does not release the customer from the obligation of performing own tests with the product selected for a specific application. While the information and suggestions are believed to be accurate and reliable, nothing stated in this bulletin is to be taken as a warranty either expressed or implied.